

AMENDMENTS

Please amend the claims as follows:

1 – 13. (Cancelled)

14. (Currently amended) A method of making a smectite clay slurry of a naturally occurring clay, comprising:

(a) dispersing one or more naturally occurring smectite clays, one or more phosphonate additives and water to form a clay slurry;

(b) shearing the clay slurry; and

(c) adjusting the pH of the clay slurry to above 5.5 ~~about 4.5~~.

15. (Previously presented) A method according to claim 14, wherein the naturally occurring smectite clay is hectorite.

16. (Previously presented) A method according to claim 14, wherein the phosphonate additive is 1-hydroxyethylene-1,1-diphosphonic acid tetra sodium salt.

17. (Previously presented) A method of making a smectite clay slurry of a naturally occurring clay according to claim 14, wherein the shearing is performed by a Gaulin homogenizer.

18-22. (Cancelled)

23. (Currently amended) A method of making a smectite clay slurry of a naturally occurring clay, comprising:

(i) dispersing one or more naturally occurring smectite clays and one or more phosphonate additives with water to form a clay slurry, wherein the phosphonate additives are selected from the group consisting of:

a) Diphosphonic acids of formula $R^1R^2C(PO(OH)_2)_2$,

b) Disphosphonic acids of formula $R^1-CR^2(PO(OH)_2)-R^3-CR^2PO(OH)_2-R^1$,

c) salts thereof, and

d) Phosphonic acid salts of formula $R^1R^4C=C(PO(OH)_2)_2$,

where R¹ is selected from the group consisting of H, a linear or branched alkyl, alkene, hydroxyalkyl, aminoalkyl, hydroxyalkene, aminoalkene with 1 to 22 carbon atoms and an aryl, hydroxyaryl, aminoaryl with 6 to 22 carbon atoms; R² is selected from the group consisting of R¹ and OH; R³ is an alkyl with 0 to 22 carbon atoms; and R⁴ is selected from the group R¹; and

(ii) shearing the clay slurry; and

(iii) adjusting ~~the~~ a pH of the clay slurry to above 5.5 ~~about 4.5~~.

24. (Cancelled)

25. (Currently amended) The method of claim 14, further comprising preparing a dry mix of the naturally occurring clay and one or more phosphonate additives prior to dispersing with water.

26. (Currently amended) The method of claim 23, further comprising preparing a dry mix of the naturally occurring clay and one or more phosphonate additives prior to dispersing with water.

27. (Previously presented) The method of claim 14 wherein at least one of the one or more naturally occurring smectite clays are sodium exchanged clays.

28. (Cancelled) The method of claim 14, further comprising adjusting the pH of the clay slurry to above about 5.5.

29. (Currently amended) The method of claim 14, further comprising adjusting the pH of the clay slurry to between ~~about 6 to~~ and 11.

30. (Currently amended) A method of making a smectite clay slurry from ~~of~~ a naturally occurring clay, comprising:

(a) dispersing one or more sodium exchanged naturally occurring smectite clays, one or more phosphonate additives and water to form a clay slurry;

(b) shearing the clay slurry; and

(c) adjusting ~~the a~~ pH of the clay slurry to above 5.5 ~~about 4.5~~.

31. (New) The method of claim 23, further comprising adjusting the pH of the clay slurry to between 6 and 11.

32. (New) The method of claim 14, wherein the pH of the clay slurry is adjusted by adding HCl, H₃PO₄, H₂SO₄, or CH₃COOH.

33. (New) The method of claim 23, wherein the pH of the clay slurry is adjusted by adding HCl, H₃PO₄, H₂SO₄, or CH₃COOH.

The Commissioner is hereby authorized by this paper to charge any fees due in connection with the filing of the response to Deposit Account No. **50-0310**.

Respectfully submitted,

February 8, 2007
Date

By: Dana Kolesar
Louis W. Beardell, Jr.
Reg. No. 40,506
Dana Kolesar
Reg. No. 55,338
MORGAN, LEWIS & BOCKIUS, LLP
1701 Market Street
Philadelphia, PA 19103-2921
Telephone: (215) 963-4764
Facsimile: (215) 963-5001